AWTA Product Testing

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client: Hurford Wholesale

400 Stapylton-Jacobs Well Road

Stapylton QLD 4207

16-005529 Test Number :

Print Date

Issue Date 10/11/2016

1/06/2017

"Premiere Oak" Clients Ref: **Sample Description**

Width

Engineered timber flooring

Colour: Natural

French Oak Veneer, plywood base Nominal Composition: Approx. 7.5kg/m2 Nominal Mass per Unit Area/Density: Nominal Thickness: Total Thickness: Approx. 13mm

AS/ISO 9239.1-2003

Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a **Radiant Heat Source**

Date of Sample Arrival 17/10/2016 **Date Tested** 09/11/2016

CHF Value	1	2	3	Mean	
Length	3.3	3.3	3.1	3.2	kW/m²
Width	≥11.0	-	-	-	kW/m²
Smoke Value	1	2	3	Mean	
Length	8	14	10	11	%.min

Blistering Yes Penetration of flame through to substrate Yes Glowing Yes Smouldering Yes

0

93250 15563 Page 1 of 2

Australian Wool testing Authority Ltd Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Chemical Testing

Mechanical Testing

Performance & Approvals Testing

: Accreditation No

: Accreditation No

Accreditation No 1356

983

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



A. JACKSON B.Sc.(Hons)

%.min

AWTA Product Testing

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client: Hurford Wholesale

400 Stapylton-Jacobs Well Road

Stapylton QLD 4207

16-005529 Test Number :

Issue Date 10/11/2016 **Print Date** 1/06/2017

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2001 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

Each specimen was clamped to a substrate of 6mm thick fibre reinforced cement board prior to testing.

93250 15563 Page 2 of 2

Australian Wool testing Authority Ltd Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Chemical Testing Mechanical Testing

Performance & Approvals Testing

: Accreditation No Accreditation No

· Accreditation No. 1356

983

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



A. JACKSON B.Sc.(Hons)

APPROVED SIGNATORY