



**Hurford Wholesale - CLIC OAK - SMOULDERED**

26 Sep 2017

**Slip Resistance Classification of New Pedestrian Surfaces - AS4586:2013 Appendix A**

Date Tested:	26 Sep 2017
Test Report Number:	KO260917-7
Client Name & Address:	Hurford Wholesale - 400 Jacobs Well Road, STAPYLTON QLD 4207
Product Tested :	CLIC OAK - SMOULDERED
Wet Pendulum Test carried out using :	Slider 96 (4S) Rubber slider
Record ambient temperature (°C)	25
Testing Officer :	Blair Ording - Munro-Stanley Portable Skid Tester #1133 - 30.08.17
Testing Officer Signature	

**Test Results :**

No. of Samples	Sample No.	Swing 1	Swing 2	Swing 3	Swing 4	Swing 5	Mean BPN of last 3 swings :	Surface Picture
5	Plank 1	32	32	31	31	30	31	
	Plank 2	34	31	31	31	31	31	
	Plank 3	32	31	30	30	30	30	
	Plank 4	35	35	32	32	32	32	
	Plank 5	35	35	35	33	33	34	

Mean BPN Slip Resistance Value (SRV)

32

CLASSIFICATION using Slider 96 (4S Slider)

P2 = 25 - 34

Accedited for Compliance with ISO/IEC 17025. The information presented herein and on the Sliptest Report is copyright and is protected by copyright law, any reproduction of this information and test report except in full is prohibited. Sliptest Australia Pty. Ltd. performed this on site test with reference to the following Australian Standard testing criteria, of AS 4586:2013 Classification of new pedestrian surface materials. Appendix A – Wet Pendulum Test Method and Hand Book HB 196: 2014 with reference to AS/NZS 4663: 2004 Slip Resistance measurement of existing pedestrian surfaces and HB 197: 1999. These results to not account for Future Wear, Maintenance or Contamination of this surface once in-situ.